

GLASSWOOL 24kg FLEXIBLE DUCTLINER

Description

Glasswool 24kg Flexible Ductliner insulation is manufactured from up to 80% recycled glass using a thermoset resin, producing fine non-combustible fibers and forming a 24kg density insulation blanket roll. A foil or decorative facing material is typically applied to one side for increased acoustic and condensation performance or when hygiene and mechanical cleaning capabilities are a requirement.

Applications

Glasswool 24kg Flexible Ductliner Insulation is suitable for use as an internal insulation for ductwork in the Heating Ventilation and Air conditioning (HVAC) Segment. Most commonly applied as an internal liner for air conditioning sheet metal ductwork. Glasswool 24kg Flexible Ductliner has an ideal combination of properties making it suitable for use with automated sheet metal cutting and ductmaking machinery. It has the high resiliency of a board, while retaining enough flexibility to be used in roll form. When used in this form, a continuous length of Glasswool 24kg Flexible Ductliner has the benefits of:

- (a) reducing wastage and;
- (b) enabling insulation of L-shaped sections by folding through 90° without cutting.

Facing Options:

A number of facing options can be applied to unfaced flexible ductliner, making it ideal for a broader range of applications:

Facing Foil Heavy Duty Perforated (HDP): Heavy Duty Perforated (HDP) Reflective Foil is most suitable in applications where a superior thermal and acoustic performance is required. Commonly used as an internal liner for rigid air-conditioning ducts. Unsuitable for use as a vapour barrier.

Facing Foil Vapastop®: Vapastop® 883 Aluminium Foil Facing is a lightweight facing most suitable in applications where a Continuous Acoustic Membrane (CAM) combined with a superior NRC acoustic performance is required. This facing option has a fully sealed and continuous membrane barrier minimising the risk of fibres entering the ducts air stream, whilst still delivering excellent acoustic absorption. Vapastop® 883 can sustain occasional mechanical cleaning.

Black Matt Facing: Black Matt Facing (BMF) is an affordable acoustic option in applications where the duct lining may be somewhat visible. It is a light duty tissue unsuitable for mechanical cleaning.

Product Data

Material R-value m ² K/W	Thickness mm	Width mm	Length m	Density kg/m ³	Weight per roll kg	Coverage m ² per roll
R2.0	70	1380	8	24	18.54	11.04
R2.0	70	1500	8	24	20.16	12
R3.0	108	1380	6	24	21.46	8.28
R3.0	108	1500	6	24	23.32	9

Note: Not all sizes may be held in stock. Contact your Baron Insulation Representative for further details.

Physical Properties

Property	Test Method/Standard	Result	Unit
Nominal density		24	kg/m³
Thermal conductivity @23°C	AS/NZS 4859.1	Complies 0.035	W/Mk
Thermal resistance @23°C	AS/NZS 4859.1	Complies	m² K/W
Moisture absorption of glasswool component		Less than 0.2% by volume	

Fire Hazard Properties

Glasswool 24kg Flexible Ductliner exhibits the following characteristics when tested in accordance with the following standards:

Property	Test Method/Standard	Test Results
		Faced with Heavy Duty (HD)
Early Fire Hazard Indices	AS/NZS 1530.3	0
Ignitability Index		0
Spread of Flame Index		0
Heat Evolved Index		0
Smoke Developed Index		2

Environmental Properties

Baron Insulation avoids the use of Ozone Depleting Potential (ODP) substances in the manufacture or composition of its FBS-1 Glasswool Bio-Soluble Insulation® and Sisalation® reflective foil products.

Health and Safety

Glasswool 24kg Flexible Ductliner is manufactured from FBS-1 Glasswool Bio-Soluble Insulation®. FBS-1 Glasswool Bio-Soluble Insulation® is safe to use and meets the criteria of the Australian Safety and Compensation Council (formerly NOHSC) to be classified as non-hazardous. Baron Insulation™ glasswool can be used with confidence in any residential, commercial or industrial application.

Technical Specification

When specifying, state the following:
The insulation material shall be Baron Glasswool 24kg Flexible Ductliner with a nominal thickness of _____mm (specify nominal thickness) faced with _____ (specify facing type) and with a material R-value of R _____m² K/W (specify material R-value).

© Baron Insulation Pty Limited 2023. Baron Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. Unless otherwise stated all ™ and ® are trademarks and registered trademarks of Baron Insulation Pty Limited ABN 99 132 459 931. BTDS_Revision_2_Issue Date_01042023

